

Patent Number(s): JP58109532-A; JP90006769-B

Title: Polyester prodn. esp. from terephthalic acid and ethylene glycol - In presence of organic poly:magnesio-siloxane!

Patent Assignee Name(s) and Code(s): NIPPON ESTER CO LTD (NPEC-C)

Derwent Primary Accession Number: 1983-731268 [32]

Patents Cited by Inventor: 0

Citing Patents: 0

Articles Cited by Inventor: 0

Patents Cited by Examiner: 0

Articles Cited by Examiner: 0

Abstract:

Polyesters are produced from (1) terephthalic acid or bifunctional carboxylic acids comprising mainly terephthalic acid, or ester-forming cpds. derived from them, and (2) ethylene glycol or glycol component comprising mainly ethylene glycol or ester-forming cpds. derived from them in the presence of (3) organic polymagnesiosiloxane.

Polyesters of high polymerisation degrees and excellent colour tone are produced in a short period of time.

Component (3) is produced, e.g. by heating dihalosilane and magnesium hydroxide in ether solvent in a stream of nitrogen. Amt. of (3) added is 0.01-10 pts.wt. per 100 pts.wt. polyester formed. The target polyester is produced e.g. by ester-exchanging dimethyl terephthalate and ethylene glycol or esterifying terephthalic acid and ethylene glycol, and polycondensing bis-(beta-hydroxyethyl) terephthalate and/or its low polymer in the presence of catalyst, e.g. antimony cpd., titanium cpd., tin cpd., pref. antimony trioxide. Pref. polyesters have limiting viscosity of 0.4-1.2 (calculated from the soln. viscosity determined in phenol-ethane tetrachloride solvent at 20 deg.C.

Drawing:

International Patent Classification: C08G-063/22

Derwent Class: A23 (Polyamides, polyesters, polycarbonates, alkyds)

Derwent Manual Code(s): A02-B; A05-E04A; A06-A00E2; A06-D; A12-W11B

Patent Details:

Patent Number	Publ. Date	Main IPC	Week	Page Count	Language
JP58109532-A	29 Jun 1983		198332	Pages: 4	
JP90006769-B	13 Feb 1990		199010		

Application Details and Date:

JP58109532-A	JP211791	24 Dec 1981
--------------	----------	-------------

Priority Application Information and Date:

JP211791	24 Dec 1981
----------	-------------